

Material No.: Code:

1.2316 X38CrMo16

DE - Brand:

R65**Chemical composition:**
(Typical analysis in %)

C	Cr	Mo					
0,38	16,50	1,20					

Steel properties:

Stainless martensitic steel with increased Cr-content for improved corrosion resistance. This grade is usually supplied in a quenched and tempered condition. Good polishability.

Applications:

Tools and moulds for corrosive plastics and polymers, food industry.

Condition of delivery:

Quenched and tempered, 280 - 325 HB
(950 - 1100 N/mm² according to DIN EN ISO 18265
Table A.1)

Physical properties:

Thermal expansion coefficient

$\left[\frac{10^{-6} \cdot \text{m}}{\text{m} \cdot \text{K}} \right]$	20-100°C	20-200°C	20-300°C	20-400°C
	10,3	10,8	11,2	11,6

Thermal conductivity

$\left[\frac{\text{W}}{\text{m} \cdot \text{K}} \right]$	20°C	350°C
	19,6	21,1

Heat treatment:

Soft annealing

Temperature	Cooling	Hardness
760 - 800°C	furnace	max. 230 HB

Stress relief annealing


The recommendation 500 - 550°C is valid for quenched and tempered condition. In the soft annealed condition stress relieving between 600 - 650°C is possible.

Temperature	Cooling
500 - 550°C	furnace


Hardening

Temperature	Cooling	Tempering
1020 - 1050°C	oil, pressure gas (N ₂), air or hot bath 500 - 550°C	see tempering diagram


(1.2316) Thermal Cycle Diagram



Continuous Cooling Transformation Diagram (CCT)



Tempering Diagram



Remarks: All technical information is for reference only.